RI. SE

Classification report – Talgø MøreTre AS

Classification report for roof exposed to external fire

MøreRoyal® Concise® Takbord

NS-EN 13501-5:2016

Author: Cristina Sanfeliu Meliá



Classification report for roof exposed to external fire



VERSION	DATE
1	2020-11-26
AUTHOR	
Cristina Sanfeliu Meliá	
CLIENT	CLIENT'S REF.
Talgø MøreTre AS	Lars Lillegård
Todalsvegen 1357	
N-6645 Todalen	
PROJECT NO.	NO. PAGES:
130003-32	4
PRODUCT	
MøreRoyal® Concise® Takbord	
ABSTRACT:	

This classification report defines the classification assigned to the product *MøreRoyal*® *Concise*® *Takbord* in accordance with the procedures given in NS-EN 13501-5:2016.

PREPARED BY Cristina Sanfeliu Meliá, MSc (Training)		FIGNATURE CRisting S.M		
CHECKED BY		SIGNATURE		
Robert Olofsson, Group manager				
APPROVED BY		SIGNATURE		
Anne Steen-Hansen, Chief Research Scientist				
REPORT NO.	CLASSIFICATION	CLASSIFICATION THIS PAGE		
130003-32	Restricted	Restricted		

RI. SE

History

VERSION	DATE	VERSION DESCRIPTION
1	2020-11-26	First version.

Contents

1	Product description					
2	2 Reports and results in support of this classification					
	2.1	Test reports	3			
	2.2	Test results	3			
3	Class	sification and field of application	4			
	3.1	Reference	4			
	3.2	Classification	4			
4	Field	l of application	4			
5	Limi	itations	4			

Product description 1

The product MøreRoyal® Concise® Takbord is described in the test report in support of the classification listed in section 2.

Reports and results in support of this classification 2

2.1 Test reports

Name of laboratory	Name of sponsor	Report ref. no. and date	Test method
RISE Fire Research AS	Talgø MøreTre AS	130004-59 2021-11-18	CEN/TS 1187:2012, Test 2. Method with burning brands and wind

Table 1 Test reports in support of this classification.

2.2 Test results

Report ref. no.: 130004-59

Test conditions:	According to CEN/TS 1187:2012, test 2. A MøreRoyal®-treated wooden (pine) roof cladding with square density between 13.5-14.5 kg/ m^2 and thickness 28 mm was tested on a substrate of expanded polystyrene (EPS).				
Test pitch:	<i>30</i> °				
Substrate:	Standard substrate; board of expanded polystyrene (EPS), density of $(20 \pm 5) \text{ kg/m}^3$, thickness of 50 mm.				

Table 2 Test results in support of the classification MøreRoyal®-treated wooden (pine) roof cladding with square density between of $13.5-14.5 \text{ kg/m}^2$ and a substrate EPS.

Parameter	Criteria		Test Results ^a				Compliance	
	Mean	Max	Test 1	Test 2	Test 3	Mean	Max	
Damaged length at 2 m/s – roof covering [m]	≤0.550	≤0.800	0.540	0.460	0.470	0.490	0.540	Yes
Damaged length at 2 m/s – substrate [m]	≤0.550	≤0.800	No damage	No damage	No damage	No damage	No damage	Yes
Damaged length at 4 m/s – roof covering [m]	≤0.550	≤0.800	0.500	0.540	0.580	0.540	0.580	Yes
Damaged length at 4 m/s - substrate [m]	≤0.550	≤0.800	No damage	No damage	No damage	No damage	No damage	Yes
^a Not for extended application.		1	<u>.</u>	1		1	1	1

3 Classification and field of application

3.1 Reference

This classification has been carried out in accordance with NS-EN 13501-5:2016.

3.2 Classification

The roof $M \phi reRoyal$ © Concise® Takbord of 13.5-14.5 kg/m² in relation to its external fire performance is classified:

$B_{ROOF}(t2)$

4 Field of application

This classification is valid for the following conditions:

- range of pitches: all pitches.
- range of substrates: - combustible and non-combustible substrates, having a density $\geq 15 \text{ kg/m}^3$.

5 Limitations

This document does not represent type approval or certification of the product

RISE Fire Research AS

Postal address: Telephone: E-mail: Internet: P. O. Box 4767 Torgarden, 7465 Trondheim +47 464 18 000 post@risefr.no www.risefr.no

